

<p>滤料: 玻璃纤维 1号</p> <p>Media: 玻璃纤维</p> <p>型号: BY-GL-633</p> <p>Item: BY-GL-633</p> <p>克重: 750±20G</p> <p>Basis Weight: 750±20G</p> <p>拉力强度:1800 N/5CM</p> <p>Breaking Strength:1800 N/5CM</p> <p>透气量:12m3/m2/min</p> <p>Air Permeability: 12m3/m2/min</p> <p>温度: 280℃</p> <p>Continuous Operating Temperature: 280℃</p> <p>瞬间运行温度: 300℃</p> <p>Maximum Surge Temperature: 300℃</p> <p>备注: 无碱膨体</p>	<p>滤料: 玻璃纤维 2号</p> <p>Media: 玻璃纤维</p> <p>型号: BY-GL-634</p> <p>Item: BY-GL-634</p> <p>克重: 750±20G</p> <p>Basis Weight: 750±20G</p> <p>拉力强度:1800 N/5CM</p> <p>Breaking Strength:1800 N/5CM</p> <p>透气量:1.5-4m3/m2/min</p> <p>Air Permeability: 1.5-4m3/m2/min</p> <p>温度: 280℃</p> <p>Continuous Operating Temperature: 280℃</p> <p>瞬间运行温度: 300℃</p> <p>Maximum Surge Temperature: 300℃</p> <p>备注: 无碱膨体覆膜</p>
<p>滤料: 玻璃纤维 3号</p> <p>Media: 玻璃纤维</p> <p>型号: BY-GL-635</p> <p>Item: BY-GL-635</p> <p>克重: 700G</p> <p>Basis Weight: 700G</p> <p>拉力强度:1600 N/5CM</p> <p>Breaking Strength:1600 N/5CM</p> <p>透气量:12m3/m2/min</p> <p>Air Permeability:12 m3/m2/min</p> <p>温度: 280℃</p> <p>Continuous Operating Temperature: 280℃</p> <p>瞬间运行温度: 300℃</p> <p>Maximum Surge Temperature: 300℃</p>	<p>滤料: 玻璃纤维 4号</p> <p>Media: 玻璃纤维</p> <p>型号: BY-GL-636</p> <p>Item: BY-GL-636</p> <p>克重: 600G</p> <p>Basis Weight: 600G</p> <p>拉力强度:1200 N/5CM</p> <p>Breaking Strength:1200 N/5CM</p> <p>透气量:12m3/m2/min</p> <p>Air Permeability:12 m3/m2/min</p> <p>温度: 280℃</p> <p>Continuous Operating Temperature: 280℃</p> <p>瞬间运行温度: 300℃</p> <p>Maximum Surge Temperature: 300℃</p>

<p>滤料: PT glass 覆膜 (GGY 水泥厂)</p> <p>Media: 玻璃纤维</p> <p>型号: BY-GL-637</p> <p>Item: BY-GL-637</p> <p>克重: 750G</p> <p>Basis Weight: 750G</p> <p>拉力强度:2000N/5CM</p> <p>Breaking Strength:2000 N/5CM</p> <p>透气量:1.5-4m3/m2/min</p> <p>Air Permeability: 1.5-4 m3/m2/min</p> <p>温度: 260℃</p> <p>Continuous Operating Temperature: 260℃</p> <p>瞬间运行温度: 280℃</p> <p>Maximum Surge Temperature: 280℃</p> <p>备注: 黄色</p>	<p>滤料: PT glass 覆膜 (GGY 电厂)</p> <p>Media: 玻璃纤维</p> <p>型号: BY-GL-638</p> <p>Item: BY-GL-638</p> <p>克重: 750G</p> <p>Basis Weight: 750G</p> <p>拉力强度:2000N/5CM</p> <p>Breaking Strength:2000 N/5CM</p> <p>透气量:1.5-4m3/m2/min</p> <p>Air Permeability: 1.5-4 m3/m2/min</p> <p>温度: 260℃</p> <p>Continuous Operating Temperature: 260℃</p> <p>瞬间运行温度: 280℃</p> <p>Maximum Surge Temperature: 280℃</p> <p>备注: 黑色耐酸处理</p>
<p>滤料: 中温玻璃纤维+涤纶</p> <p>Media: 玻纤+涤纶</p> <p>型号: BY-GL-639</p> <p>Item: BY-GL-639</p> <p>克重: 550G</p> <p>Basis Weight: 550G</p> <p>拉力强度:1200 N/5CM</p> <p>Breaking Strength:1200 N/5CM</p> <p>透气量:14m3/m2/min</p> <p>Air Permeability: 14 m3/m2/min</p> <p>温度: 150℃</p> <p>Continuous Operating Temperature: 150℃</p> <p>瞬间运行温度: 160℃</p> <p>Maximum Surge Temperature: 160℃</p>	<p>滤料: 中温玻璃纤维+涤纶</p> <p>Media: 玻纤+涤纶</p> <p>型号: BY-GL-640</p> <p>Item: BY-GL-640</p> <p>克重: 900-950G</p> <p>Basis Weight:900-950G</p> <p>拉力强度:1200 N/5CM</p> <p>Breaking Strength:1200 N/5CM</p> <p>透气量:1.5-4m3/m2/min</p> <p>Air Permeability: 1.5-4 m3/m2/min</p> <p>温度: 220℃</p> <p>Continuous Operating Temperature: 220℃</p> <p>瞬间运行温度: 260℃</p> <p>Maximum Surge Temperature: 260℃</p> <p>备注: 35-45%P84</p>