

<p> 滤料:预氧丝 型号: BY-PPS-649 Item: BY-PPS-649 克重: 680G Basis Weight:680G 拉力强度:640/540N/5CM Breaking Strength:640/540 N/5CM 透气量:14 m3/m2/min Air Permeability:14m3/m2/min 持续运行温度: 300℃ Continuous Operating Temperature: 300℃ </p>	<p> 滤料: 玄武岩 Media: Basalt 型号: BY-GL-641 Item: BY-GL-641 克重: 850-900G Basis Weight:900-950G 拉力强度:1400/1600 N/5CM Breaking Strength:1400 /1600 N/5CM 透气量:12.2m3/m2/min Air Permeability: 12.2 m3/m2/min 温度: 280-300℃ Continuous Operating Temperature: 280-300℃ 瞬间运行温度: 300℃ Maximum Surge Temperature: 300℃ </p>
<p> 滤料:PTFE 覆膜 Media:PTFE ePTFE 型号: BY-PT-617 Item: BY-PT-617 克重:750G Basis Weight:750G 拉力强度:600/800 N/5CM Breaking Strength:600/800 N/5CM 透气量:1.5-4 m3/m2/min Air Permeability:1.5-4 m3/m2/min 温度: 260℃ Continuous Operating Temperature: 260℃ 瞬间运行温度: 280℃ Maximum Surge Temperature: 280℃ </p>	<p> 滤料:P84 Media:P84 型号: BY-P84-618 Item: BY-P84-618 克重:500 G Basis Weight:500 G 拉力强度:800/1000 N/5CM Breaking Strength:800/1000 N/5CM 透气量:15 m3/m2/min Air Permeability:15 m3/m2/min 温度: 240℃ Continuous Operating Temperature: 240℃ 瞬间运行温度: 260℃ Maximum Surge Temperature: 260℃ </p>